

Postal address Swerea IVF AB Box 104 SE-431 22 MÖLNDAL Tfn +46 (0)31 706 60 00 Fax +46 (0)31 706 63		Visiting address Argongatan 30, SE- 431 53 MÖLNDAL Org. nr. 556053-1526 VAT no. SE556053-152601	
Client <b>Egida Ltd</b> <b>Krasnoborskaya 2-ya Str.</b> <b>420079 Kazan, Tartarstan, RUSSIA</b>		Client's ref. no.	
		Contact person <b>Gulnara Yakhina</b>	Our ref. no. <b>5180484-11</b>

### Object

Determination of ash content according to IKEA specification IOS-MAT-0076, version no AA-300587-6.

### Test Material

1	Material producer:	Egida Ltd
	Material description:	HS2525 polyurethane foam
	Material batch number or equivalent:	16.05.2018

The test material was received from the client 2018-06-11.

### Procedure and results

**Ash content** was determined according to ISO 1171, modified (end temperature 725°C instead of 900°C, maintained in 60 ±3 min).

Conditioning climate: (23 ±2) °C, (50 ±3) % RH

Date of test: 2018-06-13 -- 14


Table 1. Ash content

Test material	Specimen	Sample weight	Ash content
		[g]	[%]
1	1	3.16	0.06
	2	3.13	0.00
	<b>Mean value</b>		<b>0.0</b>


All results relate only to the material tested.

Mölndal, 2018-07-04

Swerea IVF



Desiré Rex  
Project leader, Foam Testing



Simonetta Granello  
Test Engineer

This report may not be reproduced other than in full, except with prior written approval of the issuing laboratory.  
General terms and conditions for Swerea IVF apply and are available on [www.swereaivf.se](http://www.swereaivf.se) or may be ordered from Swerea IVF.